

WASHINGTON STATE DEPARTMENT OF TRANSPORTATION - MATERIALS LABORATORY
PO BOX 47365 OLYMPIA, WA 98504/STREET-1655 S. 2nd AVE TUMWATER, WA 98512

BITUMINOUS SECTION TEST REPORT
TEST OF PAVING ASPHALTS

GRADE: PG64-22 Antistrip: %
SUPPLIER: SOUND Type:
SHIPPER: SOUND
DATE RECD: 07/14/2010

SR NO: COUNTY:
SECTION: OLD SR 3 TO .4 MILES OF ANDERSON HILL RD.

WORK ORDER # 007912
TRANS. LTR.# 107C89
LAB.IDENT. # 0000107C89
ASPH. LAB. # A100487
BID ITEM. # 9.02
REGION # 43

=====

ACCEPTANCE NO.	ASSURANCE NO.	CERT NO.	DATE SAMPLED
4A/4B		5674	06/30/2010

TEST: RESULTS: SPECIFICATIONS:

=====

ORIGINAL PROPERTIES:

VISCOSITY

(BROOKFIELD) @ 135 C, Pa s	3 MAXIMUM
DYNAMIC SHEAR @ 64 C, kPa	1.00 MINIMUM
C.O.C. FLASH POINT, C	230 MINIMUM

RTFO AGED PROPERTIES:

MASS LOSS AFTER RTFO, %	1.00 MAXIMUM
DYNAMIC SHEAR @ 64 C, kPa	2.20 MINIMUM
MSCR @ 3.2 kPa @ C, %	REPORT ONLY
Jnr @ 3.2 kPa @ C	REPORT ONLY
DIFFERENCE Jnr, %	REPORT ONLY

MSCR and Jnr testing performed at PG base grade temperature

PAV AGED PROPERTIES:

PAV AGING TEMPERATURE C	
DYNAMIC SHEAR @ 25 C, kPa	5000 MAXIMUM
DYNAMIC SHEAR @ 22 C, kPa	REPORT ONLY
CREEP STIFFNESS @ -12 C	
"S", MPa	300 MAXIMUM
"m"	0.300 MINIMUM

=====

OSC LABORATORY:

Materials File X
General File X

REGION: OLYMPIC

Construction Engineer 43 X
Materials Engineer 43 X

PE: J. MOORE X(2)
SOUND X

Material does MEET
specification requirements.

Remarks:

SAMPLE APPROVED FOR USE ON THIS
CONTRACT BASED ON PREVIOUS AND
SUBSEQUENT PASSING TEST
RESULTS.

THOMAS E. BAKER, P.E.
Materials Engineer

By: Joseph R. DeVol

Date 07/26/2010
Telephone 360-709-5421

T-119	T-126
T-120	T-132
T-121	T-133
T-124	T-136
T-130	
T-131	
T-134	
T-173	1